

Technical Information

Wanda 180 Accelerator

– W1.08.05



Wanda 180 Accelerator is developed to improve the through-hardening and to decrease the drying time of Wanda clearcoats described below, suitable for spot- and panel repairs.

Do not use 180 Accelerator in application temperatures over 25°C.

800 Clear VHS



Mixing ratio

2: 800 Clear VHS
1: 330 Hardener HS
10%: 180 Accelerator



Mixing stick

Use Wanda measuring stick
W2

810 Clear AS



Mixing ratio

2: 810 Clear AS
1: 300 Hardener Slow / 310 Hardener Standard / 320 Hardener Rapid
10%: 180 Accelerator



Mixing stick

Use Wanda measuring stick
W2

820 Clear AS Express



Mixing ratio

2: 820 Clear AS Express
1: 310 Hardener Standard / 320 Hardener Rapid
10-20%: 180 Accelerator



Mixing stick

Use Wanda measuring stick
W3

Technical Information

Wanda 180 Accelerator

– W1.08.05



Equipment

Spray gun set-up: 1.2-1.4 mm

Application pressure: 1.7-2.2 bar

*See user manual spray gun

Product storage

Avoid extreme temperature fluctuation.

Shelf life

Product shelf-life is determined when products are stored unopened
180 Accelerator: 2 years at 20°C

Akzo Nobel Car Refinishes B.V.
Address: Rijksstraatweg 31, PO Box 3, 2170 BA Sassenheim
Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3, 2170 BA Sassenheim, The Netherlands. www.Wandarefinish.com