


Technical Information

Wanda 170 Thinner Fade Out RTS —W9.01.01



170 Thinner Fade Out RTS is a ready to spray aerosol designed for dissolving overspray while blending top/clearcoats and avoids the need for painting whole parts. The Ideal solution for creating spot-repairs. The preparation and application method and technique described below is appropriate for spots and blends with all Wanda Topcoats and Clearcoats.



Blend area preparation



Polishing

Thoroughly polish the blending area with abrasive polishing compound, preferably in combination with a polishing machine.

Optional: the blend area can be treated with very fine abrasive like P2000-P3000 or comparable.



Surface cleaning

Remove any surface contamination with an appropriate surface cleaner prior to clearcoat / topcoat application.

Ensure it is thoroughly cleaned and wiped dry with high performance surface cleaning cloths.

Technical Information

Wanda 170 Thinner Fade Out RTS —W9.01.01




Blending application



Application

Apply clearcoat / topcoat according to TDS recommendation
Extend the 2nd coat beyond the 1st coat



Flash-off

No flash-off is needed, directly continue with next steps



170 Thinner Fade Out is ready for use



Application

Apply 1-3 thin coats on the blending area, extending forward into the polished area.
Allow for approximately 15-30 seconds flash-off time between layers.

Drying



Drying

Dry the clearcoat / topcoat according to product TDS recommendations.
Let the object cool down to ambient temperature prior to polishing



Infra-Red

Additional drying by infra-red will secure optimum through hardening in the blend area.

Technical Information

Wanda 170 Thinner Fade Out RTS —W9.01.01



Polishing of the blended area



Polishing

Polish the blended area by hand or machine using a fine polishing compound. Use coarser polishing compound in case more effort is needed.

Polishing by machine using a soft compound pad at low rotation speed, use a hard pad in case more effort is needed.

Suitable Products

170 Thinner Fade Out RTS can be used with all Wanda clearcoats and topcoats

Akzo Nobel Car Refinishes B.V.
Address: Rijksstraatweg 31, PO Box 3, 2170 BA Sassenheim
Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3, 2170 BA Sassenheim, The Netherlands. www.Wandarefinish.com