

Technical Information

Wanda 800 Clear VHS

—W1.05.03



A top-quality gloss finish can be easily achieved with Wanda 800 Clear VHS. This VOC-compliant clearcoat performs brilliantly in all kind of repairs from small spot to total resprays. It offers excellent overall results.




Mixing ratio

2: 800 Clear VHS
1: 330 Hardener HS
10%: 130 Thinner HT / 140 Thinner HS / 180 Accelerator



Mixing stick

Use Wanda measuring stick
W2




Equipment

Spray gun set-up: 1.2-1.4 mm
Application pressure: 1.7-2.2 bar
*See user manual spray gun



Application

2 x 1 coat



Flash-off

Between coats: 3-10 minutes
Before curing: 5-10 minutes



Drying

130 Thinner HT:	20°C	6 hours
140 Thinner HS:		2 hours
180 Accelerator		45 minutes

60°C

40 minutes*
30 minutes*
15 minutes*
*object temperature



Protection

Use suitable respiratory protection.
AkzoNobel Vehicle Refinishes recommends the use of a fresh air supply respirator.

Technical Information

Wanda 800 Clear VHS

—W1.05.03



Product and Additives	800 Clear VHS 330 Hardener HS 130 Thinner HT 140 Thinner HS 180 Accelerator		
Basic Raw Materials	800 Clear VHS: Hardener:	Acrylic resins Poly-isocyanate resins	
Suitable substrates	Original finishes Wandabase WB		
Mixing Ratio	2: 800 Clear VHS 1: 330 Hardener HS 10%: 130 Thinner HT / 140 Thinner HS / 180 Accelerator Use measuring stick W2		
Viscosity	16-18 seconds DIN Cup 4 at 20°C		
Potlife	130 Thinner HT 140 Thinner HS 180 Accelerator	2 hours at 20°C 30-45 minutes at 20°C 30-45 minutes at 20°C	
Spray gun set up and application pressure	Gravity feed	Fluid tip 1.2-1.4 mm	Pressure 1.7-2.2 bar* HVLP max 0.7 at air cap *See user manual spray gun used
Application	Apply a flowing closed coat, allowing for a 3-10 minutes flash-off time at 20°C. Next, apply a full flowing coat allowing for a 5-10 minutes flash-off time at 20°C before bake.		
Cleaning of equipment	Use Wandabase Guncleaner		
Film thickness	Recommended application (2 coats)		45-60 µm
Drying times	20°C		60°C
	130 Thinner HT		
	Dust dry	90 minutes	15 minutes
	Dry to handle	6 hours	40 minutes
	140 Thinner HS		
	Dust dry	60 minutes	10 minutes
	Dry to handle	2 hours	30 minutes
	180 Accelerator		
	Dust dry	25 minutes	10 minutes
	Dry to handle	45 minutes	15 minutes

Technical Information

Wanda 800 Clear VHS

—W1.05.03



	Infra-red	5 minutes low power	8 minutes low power
Theoretical coverage	Ready for use mixture at 1 micron layer thickness: $\pm 522 \text{ m}^2/\text{liter}$ The practical coverage depends on many factors i.e. shape of the object, roughness of the surface, application method and application circumstances.		
Polishability	Ready to polish minimum 1 hour after cooling down.		
Product storage	Avoid extreme temperature fluctuation.		
Shelf life	Product shelf life is determined when products are stored unopened 800 Clear VHS: 1 year at 20°C		
VOC	2004/42/II B(d)(420)420 The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/liter VOC. The VOC content of this product in ready to use form is max. 420 g/liter.		

Akzo Nobel Car Refinishes B.V.
Address: Rijksstraatweg 31, PO Box 3, 2170 BA Sassenheim
Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3, 2170 BA Sassenheim, The Netherlands. www.Wandarefinish.com